



Turbine Oil

Description

The BP Energol THB turbine oil range of lubricants are based upon highly refined mineral oil enhanced with rust and oxidation inhibitiors.

Application

Energol THB turbine oils are formulated using highly refined mineral oils, with selected additives to improve their inherent high oxidation stability and to protect against corrosion of ferrous and non ferrous metals. Energol THB oils are primarily intended for the lubrication of gas and steam turbines where the base oils used have been selected to give the requisite water separation characteristics as well as providing resistance to foaming and air entrainment, all essential properties for this demanding application.

Energol THB grades can also be used as a general purpose rust and oxidation (R&O) lubricant for compressors, hydraulic systems, gear boxes and circulatory systems where high oxidation stability performance is required but with no demand for antiwear performance.

Energol THB is fully compatible with nitrile, silicone and fluropolymer seal materials.

Main Performance Features

Excellent oxidation stability provides trouble free operation for extended periods in aggressive environments where heat, air, moisture and metals can all contribute to oil degradation.

Good foam and air release properties mean the product meets the requirements of most turbine builders. Excellent water separation and corrosion inhibition means reduced down time through prolonged lubricant life and increased equipment reliability.

Typical Characteristics

| Name | Method | Units | Energol THB 150 |
|-----------------------------------|------------|---------|-----------------|
| Density @ 15°C | ASTM D4052 | g/ml | 0.886 |
| Kinematic Viscosity @ 40°C | IP 71 | mm²/s | 150 |
| Kinematic Viscosity @ 100°C | IP 71 | mm²/s | 14.5 |
| Viscosity Index | ASTM D2270 | | 97 |
| Foam Sequence I, Tendency | IP146 | ml | 20 |
| Foam Sequence I, Stability | IP146 | ml | 0 |
| Air Release Value @ 50°C | IP 313 | mins | 10 |
| Demulsification | IP 19 | seconds | 90 |
| Pour Point | IP 15 | °C | -12 |
| Flash Point | IP 34 | °C | 230 |
| Rust Test | IP 135 B | - | Pass |
| RPVOT | ASTM D2272 | mins | 450 |
| Copper Corrosion, 3 hours @ 100°C | IP 154 | - | 1A |
| TOST to 2 mgKOH/g | ASTM D943 | hours | 4000 |

Care and Handling

Avoid prolonged or repeated contact with skin. Wash thoroughly after handling.

Packaging and Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and the obliteration of drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing conditions.



This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Marine, Technology Centre, Whitchurch Hill, Pangbourne, Reading RG8 7QR, United Kingdom

www.bpmarine.com

